

**Technical data sheet**

Heterogeneous synthetic flooring  
with PU surface treatment acc. to EN ISO 10582



Attributes	Standard	Measure	DRYBACK	DRYBACK	DRYBACK
Thickness of wear layer	ISO 24340	mm	0,30	0,30	0,55
Bevel edge	Depending on the decor		no	no	yes
Total thickness approx.	ISO 24346	mm	2,0	2,5	2,5
Residual indentation approx.	EN ISO 24343-1	mm	≤ 0,1	≤ 0,1	≤ 0,1
Suitable for castor chairs	EN 425 / ISO 4918		yes	yes	yes
Suitable for under floor heating			yes	yes	yes
Thermal insulation resistance approx.	EN 12667	m² K/W	~ 0,02	~ 0,03	~ 0,02
Impact sound insulation approx.	EN ISO 16251-1	dB	~ 4	~ 4	~ 4
Fire behaviour	EN 13501-1		Bfl-s1	Bfl-s1	Bfl-s1
Dimensional stability approx.	EN ISO 23999	%	~ 0,1	~ 0,1	~ 0,1
Light fastness	EN ISO 105-B02		≥ 6	≥ 6	≥ 6
Resistance to chemicals *1			given *1	given *1	given *1
Non-slip safety			R 10 **2	R 10 **2	R 10 **2
Slip resistance			DS	DS	DS
Ranges of use	EN ISO 10874		21-23 + 31	21-23 + 31	23-33 + 42
Sizes / Packaging unit			914,4 x 152,4 mm 1219,2 x 228,6 mm	27 Planks - 3,76 m² 16 Planks - 4,46 m²	

\*1 in cases of short-term exposure to common household products  
\*\*2 at plain surface: R 9

Please consider our fitting and maintenance instructions.

Wear layer:

0,30 mm Dryback



0,55 mm Dryback



with bevel edge depending on decor



Emission gepr. Üfter Bodenbelag

Subject to technical changes!

Stand: 07/2016\_Rev01

China Head Office:

ZHANGJIAGANG KING PLASTICS CO., LTD | 1701, Huajian Bldg, Shazhou Road(W), Zhangjiagang | China  
Tel. 0086 (512) 58988009 | Fax 0086 (512) 58988018 | E-Mail: jed@fondi.com.cn | Internet: www.jimpa.dk

Danmark Branch:

MIH store Aps | Marius Pedersens Vej 26 | 4300 Holbæk | Danmark  
Tel. 0045-81716171 | E-Mail: info@mih-store.com

Czech Branch:

R.P.I. REAL spol. s r.o. | Sokolovská 1007 | 33441 Dobřany | Czech Republic  
Tel. 0420-77710443 | E-Mail: info@bolta.cz